

EASY AS ONE, TWO AND THREE

"n2thenix" bags are water soluble and can be added to the agitator intact.


1. Add two thirds of the desired water content to agitator, and add the colour through bags at the correct dosage rate. Refer to the dosage sheets to determine the correct quantity of bags that are required to achieve the desired colour.

2. Mix at full mixing speed for a minimum of one minute then add the dry ingredients (e.g cement, aggregates, and required admixtures) to the agitator.

3. Add the balance of the water to bring the concrete up to the desired slump. Mix Concrete for a minimum of 10 minutes to fully disperse colour... That's it.



UV RESISTANT, EVERYDAY COLOUR FOR GREY CEMENT



BEIGE BUFF (2)



BRICKTONE (1)



CHARCOAL (1)




CYPRESS GARDEN (1)



DESERT SPICE (1)



EXPRESSO (2)



GRAPE (1)




HERITAGE RED (2)



LATTE (2)




LEAD (2)



LIGHT RUBY (2)




LIGHT TERRACOTTA (1)



MIDNIGHT (2)



MIST GREEN (1)



PALE GREY (1)



PAPERBARK (1)




PEBBLE SAND (1)



SAHARA RED (2)



STONE (1)



TAHINI (1)



TAN (1)



TERRACOTTA (2)



WHEAT (1)



WILD MUSTARD (2)

Colour quantity based on addition to 25 – 32 MPA Grey Concrete. (1) 1 x 10kg bag per cubic metre (2) 2 x 10kg bags per cubic metre

